

■ SUITABILITY AREA PRODUCT & COMPOSITION GUIDE

REFERENCE	WALL	FLOOR	WET AREAS	POOLS	MATERIAL
Arezzo	Int/Ext	No	Yes	No	Glass Gold
Elba	Int/Ext	No	Yes	No	Glass Gold
Firenze	Int/Ext	No	Yes	No	Glass Gold
Lucca	Int	No	No	No	Glass Gold & Resins
Zambra, Vinci, Forli	Int/Ext	Residential	Yes	Yes	Glass
Pisa, Livorno	Int/Ext	Residential	No	No	Glass Resins

■ TECHNICAL CHARACTERISTICS

TEST UNE-EN-ISO 10545-3 WATER ABSORPTION	TEST UNE-EN-ISO-101-92=101 SURFACE HARDNESS. MOSH.	TEST UNE-EN-ISO 10545-9 RESISTANCE TO THERMAL SHOCKS	TEST UNE-EN-ISO 10545-12 FROST RESISTANCE	TEST UNE-EN-ISO 10545-13:1998 RESISTANCE TO CHEMICAL ATTACK			
				DOMESTIC PRODUCTS	POOL WATER ADDITIVES	LOW ACID AND ALKALINS	HIGH ACID AND ALKALINS
None	4	Resistant	Resistant	GA	-	-	-
TEST UNE-EN-ISO 10545-14 RESISTANCE TO STAINING	TEST UNE-EN-ISO 10545- 11=1997 CRACKING	DIN 51094 COLOUR STABILITY ON EXPOSURE TO LIGHT AND UV RAYS	DCOF WET DYNAMIC COEFFICIENT OF FRICTION ANSI A 137.1 STANDARD		DIN 51130:2004 SLIP RESISTANCE WEARING SHOES	DIN 51097 SLIP RESISTANCE IN BARE FEET	TEST UNE-ENV 12633:2003 (CTE) ANTI SKID COEFFICIENT, SUITABLE FOR OUTDOOR USE AND SWIMMING POOLS
Class 5	Resistant	Resistant	-		-	-	-

■ PACKING

SHEET HOJA	BOX CAJA	PALLET PALET	EURO PALLET EURO PALET
Size / Dimensión: 311x311 mm (12.24"x12.24")	Sheets / Hojas: 5	Quantity / Cantidad: 105,84 m ² (1,139 sqft)	Quantity / Cantidad: 70,56 m ² (759.5 sqft)
Thickness / Espesor: 4,9 mm (0.19")	Quantity / Cantidad: 0,49 m ² (5.27 sqft)	Boxes / Cajas: 216	Boxes / Cajas: 144
Weight / Peso: 0,91 Kg (2.01 lb)	Weight / Peso: 4,57 Kg (10.1 lb)	Gross weight / Peso bruto: 987,12 Kg (2,175 lb)	Gross weight / Peso bruto: 658 Kg (1,450 lb)



*Minimum
Order*
1 module / 1 Box



*Sales
Unit*
Square meters



*Mosaic
Support*
MESH

All ONIX 98 % recycled glass mosaics series are made of molten glass. Molten glass characteristics may include irregular edges and small variations in size. These characteristics are inherent to the product and to the standard production. The small size and shape variations can affect the grout joint appearance and enhance the natural aspect of these products.