













GEMSTONE

Imballi - Packing - Verpackung - Emballage - Embalaje				DIGITAL TECHNOLOGY	PORCELLANATO IMPASTO COLORATO	GEMSTONE	
Formato Size Format Formato	Pezzi/Scatola Pieces/Box Stück/Karton Pieces/Boîte Piezas/Caja	Mq./Scatola Sqm./Box Qm./Karton M ² /Boîte Mq./Caja	Kg./Scatola Kg./Box Kg./Karton Kg./Boîte Kg./Caja	Scatole/Pallet Boxes/Pallet Kartons/Palette Boîte/Palette Caja/Pallet	Mq./Pallet Sqm./Pallet Qm./Palette M ² /Palette Mq./Pallet	Kg./Pallet Kg./Pallet Kg./Palette Kg./Palette Kg./Pallet	Spessore Thickness Stärke Epaisseurs Espesor
58,5x117,2 rett.	2	1,380	34,56	36	49,68	1259	10,5 mm
58,5x117,2 lux	2	1,380	34,56	36	49,68	1259	10,5 mm
58,5x58,5 rett.	4	1,380	34,00	30	41,40	1035	10 mm
58,5x58,5 lux	4	1,380	34,00	30	41,40	1035	10 mm
29,1x58,5 rett.	5	0,860	21,61	48	41,28	1052	10 mm
29,1x58,5 lux	5	0,860	21,61	48	41,28	1052	10 mm
7,1x29,1 rett.	44	0,938	20,80	44	41,27	935	10 mm
7,1x29,1 lux	44	0,938	20,80	44	41,27	935	10 mm
29,1x29,1 mix rett.	4	-	-	-	-	-	-
29,1x29,1 mix lux	4	-	-	-	-	-	-
30x33 liscia rett.	4	-	-	-	-	-	-
30x33 liscia lux	4	-	-	-	-	-	-
1,5x58,5 coprispigolo	6	-	-	-	-	-	-
9x58,5 battiscopa rett.	12	-	-	-	-	-	-
9x58,5 battiscopa lux	12	-	-	-	-	-	-

Dati tecnici secondo norme - Tecnical data conform to Caractéristiques techniques d'après normes Technische Daten nach den Normen

EN 14411 B I, GL

GEMSTONE

Caratteristica tecnica Technical data Caractéristiques techniques Technische Daten	Norme Norms Normes Norm	Valori ascot Value ascot Valeur ascot Wert ascot	Caratteristica tecnica Technical data Caractéristiques techniques Technische Daten	Norme Norms Normes Norm	Valori ascot Value ascot Valeur ascot Wert ascot
 Resistenza all'abrasione Abrasion resistance Résistance à l'abrasion Abrasionswiderständigkeit	ISO 10545-7	PEI IV	 Resistenza attacco chimico Chemical resistance Résistance chimique Chemische beständigkeit	ISO 10545-13	Resiste Resists Resiste Bestanding
 Assorbimento d'acqua Water absorption Absorbition d'eau Wasseraufnahme	ISO 10545-3	≤ 0,5 %	 Resistenza alle macchie Stain resistance Résistance aux taches Fleckenfestigkeit	ISO 10545-14	Totale Complete Totale Absolut
 Resistenza alla flessione Breaking modulus Résistance à la flexion Biegefestigkeit	ISO 10545-4	40±55 N/mm²	 Resistenza al gelo Resistance to frost Résistance au gel Frostbeständigkeit	ISO 10545-12	Non gelive Frost proof Ingelif Frostsicher
 Durezza Mohs Mohs hardness Dureté Mohs Haerte Mohs	UNI 101	5	 Scivolosità Slipperiness Degré de glissement Rutschhemmung	ANSI A137-1	> 0,42
 Scivolosità Slipperiness Degré de glissement Rutschhemmung	DIN 51130	R 10	 Resistenza allo scivolamento Slip resistance Résistance au glissement Rutschhemmung	DIN 51097	A + B
 Scivolamento B.C.R.A. Slipperiness B.C.R.A. Degré de glissement B.C.R.A. Rutschhemmung B.C.R.A.	TORTUS	WET > 0,53 DRY > 0,49	 Stonilizzazione Shading Denuançage Spielfarbig		V3