









# TECHNICAL DATA

<b>MANUFACTURER</b>	MAX GLORY	Classification test	—
<b>PRODUCT NAME MODEL AND SIZE TRADEMARK / GRADE</b>	<b>URBAN MAX</b> Porcelain tiles 3" x 6" - 149mm x 74mm		
<b>SOURCE SAMPLE</b>	glazed tile	—	—
<b>CONFIDENT DEPARTMENT ADDRESS</b>		Sample quantity	15 pieces
<b>MANUFACTURER (PROVIDED BY THE APPLICANT)</b>		Reception date	2014-02-01
<b>TEST STANDARD</b>	EN 14411:2012 Ceramic tiles. Appendix K required for Group tiles B III ( $E_b > 10\%$ )		
<b>CONCLUSION OF TEST</b>	The results conform to the requirement of Annex L of standard EN 14411: 2006 with respect to the test items.  <b>Note:</b> Any duplicate copy will not be valid without a red stamp, re-seal especially for inspection.		

TEST ITEM		TEST METHOD	TECHNICAL PREREQUISITES	RESULTS
Length		EN ISO 10545-2	$\pm 0.5\%$	+0.15% ~ 0.019%
			$\pm 2.0 \text{ mm}$	+0.1mm ~ +0.3 mm
Width		EN ISO 10545-2	$\pm 0.75 \text{ mm}$	+0.2 mm ~ +0.4 mm
Thickness		EN ISO 10545-2	7.7 mm $\pm 0.5 \text{ mm}$	0 ~ +0.1 mm

# TECHNICAL DATA

TEST ITEM		TEST METHOD	TECHNICAL PREREQUISITES	RESULTS
Water absorption		EN ISO 10545-3	$E_b > 10\%$	16.6%
			Min. 9%	+16.3% ~ 16.9%
Breaking strength		EN ISO 10545-4	$\geq 200$	606
Modulus of rupture			$\geq 12$	23,5
Resistance to thermal shock		EN ISO 10545-9	—	Complete resistance
Crazing resistance		EN ISO 10545-11	—	Complete resistance
Reaction to fire		CWT	Class A1 or A1 <sub>FL</sub>	Yes
Resistance to stain		EN ISO 10545-14	Minimum class 3	Class 5
Resistance to chemicals and additives for swimming pools		EN ISO 10545-13	Minimum class B	GA
Resistance to acids and alkalis at low concentrations		EN ISO 10545-13	Declared value	GLA
Resistance to acids and alkalis high concentration		EN ISO 10545-13	Declared value	GHA